

Revision date: March-2007

## SPECIFICATION SHEET

CAS No. 1309-48-4

### MAGNESIUM OXIDE REMAG MG

Property	Analysis % max
<b>CaO</b>	<b>1.10</b>
<b>SiO<sub>2</sub></b>	<b>0.25</b>
<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.20</b>
<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.20</b>
<b>MgO</b>	<b>97.5min</b> by difference
<b>L.O.I.</b>	<b>10.50</b>
<b>Screen analysis:</b>	
<b>Plus 100 mesh</b>	<b>1.0 % max</b>
<b>-100 mesh +140</b>	<b>4.0% max</b>
<b>Minus 140 mesh</b>	<b>95.0 % max</b>

Note: All this information is based upon our own analysis and research which are believed to be accurate. However, no warranty is made of same, considering the various analytical methods. Neither is warranty made of the end use results, since we cannot cover every possible application or different handling of this product